FEATURES AND BENEFITS


- Designed to close gaps in roof & sidewall applications. Material is pre-cut to conform to metal panel configurations.
- Applications include closing the openings at the ridge (peak of the building) or at the eave (gutter-line of a building).
- 1.8 lb. Density polyethylene foam is designed to withstand harsh weather elements including moisture & ultraviolet rays.
- Optional pre-applied adhesive helps to keep closure in place before roof panel is fastened.
- Interlocking dovetails provide a secure end to-end fit, eliminating any potential gaps
- Other profiles are available. Call ST Fastening Systems Customer Service for availability.

| DESCRIPTION | PITCH OF CORR | WIDTH OF STRIP | HEIGHT OF CORR | LENGTH OF STRIP | PIECES PER CTNL | WEIGHT PER CTN. |
|----------------------------|---------------------|----------------------|-------------------|-----------------------|-----------------------|-----------------------|
| 3/4" Ag Rib | 9" | 7/8 | 3/4" | 36" | 100 | 6 LBS. |
| R-Panel | 12" | 7/8 | 1-1/4" | 36" | 100 | 8 LBS. |
| U-Panel | 6" | 7/8 | 3/4" | 36" | 100 | 6 LBS. |
| Pro Panel II | 9" | 7/8 | 5/8" | 36" | 100 | 8 LBS. |
| 2.67" x 7/8" Corrugated | 2.87" | 7/8 | 7/8" | 36" | 100 | 6 LBS. |


| ST Closure Strips | | |
|---|-------------------|-----------------------|
| Physical Properties | TEST METHODS | REQUIREMENT |
| Density (lb./cf) | ASTM D 3574 | 1.8 - 2.0 |
| 110 mph Wind Driven Rain Test | AS 100(A) | NA |
| Air Permeability (ft3/m./ft2 of Surface) | ASTM D737 | NA |
| Tear Resistance (lb./ln. min.) | ASTM D 3574 | 6 machine direction |
| | ASTM D 3574 | 11 cross direction |
| Tensile Strength (lbs/in2 min.) | ASTM D 3574 | 60 machine direction |
| | ASTM D 3574 | 38 cross direction |
| Compress Force Deflection (lbs/in2 @ 25%) | ASTM D 3574 | 5 |
| Compress Force Deflection (lbs/in2 @ 50%) | ASTM D 3574 | 15 |
| Compression Set (% Original Thickness) | ASTM D 3574 | 24 - 28 |
| Elongation (% min.) | ASTM D 3574 | 124 machine direction |
| | | 88 Cross Direction |
| Shore Hardness (00 Scale) | ASTM 2240 | 51 |
| Thermal Stability (% Max) | Machine Direction | -2.0 |
| (24 hour @ 158oF) | Cross Direction | -1.0 |
| Thermal Conductivity (K Factor) | ASTM C177 | 0.25 |
| BTU in./F Hr oF | | |
| Water Absorption (Lbs/SqFt Cut Surface) | ASTM D-1667 | 0.04 |
| Working Temperature Range (Fo) | | -40 to 160 |
| Flammability | AVSS 302 | Pass |

STClosureStrips











Pre-applied adhesive helps to keep closure in place before roof panel is fastened

KILLIAN'S CUSTOM METAL I
ROOFING & PANEL LLC

